

PURLIN GLIDE

Coating Thickness:	1.75/1.1 mil average
Weight:	3.4 oz. per square yard
Tensile Strength:	115 lbs. warp x 65 lbs. weft (ASTM D 5034)
Tongue Tear:	22 lbs. warp x 18 lbs. weft (ASTM D 2261)
Puncture Resistance:	43 lbs. (ASTM D 4833)
Permeance:	0.02 (ASTM E 96 A&B)
Light Reflectance:	>80% (ASTM E 1347)
Mullen Burst:	165 psi (ASTM D 3786)
Flame Resistance:	Flame Spread - 10 Smoke Developed - 30 (ASTM E 84 & UL 723)
UV Weathering:	UV stabilizers added for extra protection

**PLEASE CONTACT YOUR SILVERCOTE SALES REPRESENTATIVE
FOR MORE INFORMATION AT (844) 232-3701 OR INFO@SILVERCOTE.COM**